GENIEMAT® RST15 Sound Control Underlayment



Product Specification	
Product Name:	GenieMat RST15
Dimension:	Rollgood: 1.22 m wide, 3.05 m long (4' wide, 10' long)
Coverage:	3.72 m²
Thickness:	nom. 15 mm (5/8")
Density:	Shall be > 1000 kg/m^3
Roll Weight:	54 kg
Technical Data	
HIIC: (ASTM WK59631)	Shall be \geq 60 when tested on a 203 mm (8") concrete slab with vinyl Shall be \geq 59 when tested on a 203 mm (8") concrete slab with wood
Building code	Meets and improves on Approved Document E impact performance requirements by 10 dB when used under LVT or hardwood flooring. Meets and exceeds on BCA part F5 impact performance requirements
Point Load Test for Crack Isolation Membranes: (ANSI 118.12)	Exceeds pass criteria
Puncture Testing When Installed Under Luxury Vinyl Tile: (ASTM F924)	No change when compared to puncture failure limit of luxury vinyl tile tested without underlayment
Resistance to Impact When Installed Under Luxury Vinyl Tile: (ASTM F1265)	Luxury vinyl tile shows no signs of breaking of cracking and meets standard criteria
Rolling Load Indentation When Installed Under Luxury Vinyl Tile: (ASTM F2753)	Luxury vinyl tile shows no signs of indentation and plank separation for 12,500 cycles







[©] Pliteq Inc. 2019.

^{*}TM Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue. However, we reserve the right to make changes when necessary without further notification. Suggested application may need to be modified to conform with local building codes and conditions. We cannot accept responsibility for products that are not used, or installed, to our specifications. All listed dimensions are nominal.

GENIEMAT® RST15 Sound Control Underlayment



Technical Data

Temperature Stability: $-40^{\circ}\text{C to } +115^{\circ}\text{C } (-40^{\circ}\text{F to } +240^{\circ}\text{F})$

Thermal resistance

(R-value): 0.113 (m²K)/W

Thermal transmittance

(U-value): $8.867 \text{ W/(m}^2\text{K)}$















AROUND THE WORLD.



PLITEQ INC.

131 Royal Group Crescent Vaughan, ON L4H 1X9 Canada

T. + 1 416 449 0049

info@pliteq.com www.pliteq.com

PLITEQ (UK) LTD.

Irongate House 22-30 Dukes Place London EC3A 7LP

T. + 44 203 9846444

info@pliteq.co.uk www.pliteq.co.uk

PLITEQ BUILDING MATERIALS TRADING LLC.

European Business Centre Dubai Investment Park PO Box 473 512 Dubai, UAE

T: +971 4 567 4944

info@pliteq.ae www.pliteq.ae

PLITEQ ASIA PACIFIC PTE LTD.

101 Cecil Street #19-13 Tong Eng Building Singapore 069533

T. +65 8452 6865

info@pliteq.sg www.pliteq.sg





























© Pliteq Inc.

Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue.

Trademarks of Pliteq Inc. The information provided is accurate to the best of our knowledge at the time of issue. may need to be modified to conform with local building codes and conditions. We cannot accept responsibility for products that are not used, or installed, to our specifications. All listed dimensions are nominal.